



Quantum Spin Hall Effect in Three Dimensional Materials: Lattice Computation of Z_2 Topological Invariants and Its Application to Bi and Sb

Takahiro FUKUI and Yasuhiro HATSUGAI¹

¹Department of Mathematical Sciences, Ibaraki University, Mito 310-8512

¹Department of Applied Physics, University of Tokyo, Tokyo 113-8656

(Received March 1, 2007; accepted March 12, 2007; published April 25, 2007)

We derive an efficient formula for Z_2 topological invariants characterizing the quantum spin Hall effect. It is defined in a lattice Brillouin zone, which enables us to implement numerical calculations for realistic models even in three dimensions. Based on this, we study the quantum spin Hall effect in Bi and Sb in quasi-two and three dimensions using a tight-binding model.

KEYWORDS: Quantum spin Hall effect, Time reversal symmetry, Z_2 topological invariant, Chern number, Lattice gauge theory

DOI: [10.1143/JPSJ.76.053702](https://doi.org/10.1143/JPSJ.76.053702)

Quantum spin Hall (QSH) effect¹⁻⁵⁾ has been attracting much current interest as a new device of spintronics.⁶⁻⁹⁾ It is a topological insulator¹⁰⁻¹²⁾ analogous to the quantum Hall (QH) effect, but it is realized in time-reversal (\mathcal{T}) invariant systems. While QH states are specified by Chern numbers,^{13,14)} QSH states are characterized by Z_2 topological numbers,²⁾ which suggests that Z_2 invariants would have deep relationship with the Z_2 anomaly of the Majorana fermions.^{15,16)}

Graphene has been expected to be in the QSH phase.^{1,2)} However, recent calculations have suggested that the spin-orbit coupling in graphene is too small to reveal the QSH effect experimentally.^{17,18)} Recently, it has been pointed out that Bi thin film is another plausible material for QSH effect.¹⁹⁾ Also by the idea of adiabatic deformation of the diamond lattice, it has been conjectured that Bi in three dimensions (3D) is in a topological phase.²⁰⁾

While systems in two dimensions (2D) are characterized by a single Z_2 topological invariant, four independent Z_2 invariants are needed in 3D.²⁰⁻²³⁾ This makes it difficult to investigate realistic models, in which complicated many-band structure is involved. Therefore, for the direct study of Bi in 3D as well as for the search for other materials, to establish a simple and efficient computational method of Z_2 invariants in 3D is an urgent issue to be resolved.

In this paper, we present a method of computing Z_2 invariants based on the formula derived by Fu and Kane²⁴⁾ together with the recent development of computing Chern numbers in a lattice Brillouin zone.²⁵⁻²⁷⁾ This method is based on recent developments in lattice gauge theories³⁰⁻³⁵⁾ but simple enough to compute Z_2 invariants even for realistic 3D systems. Based on this, we study a tight-binding model for Bi and Sb.

First, we derive a lattice version of the Fu-Kane formula.²⁴⁾ To this end, we restrict our discussions, for simplicity, to systems in 2D, where a single Z_2 invariant is relevant. Let \mathcal{T} be the time-reversal transformation $\mathcal{T} = i\sigma^2 K$, and assume that the Hamiltonian in the momentum space $\mathcal{H}(k)$ transforms under \mathcal{T} as $\mathcal{T}\mathcal{H}(k)\mathcal{T}^{-1} = \mathcal{H}(-k)$. Let $\psi(k) = (|1(k)\rangle, \dots, |2M(k)\rangle)$ denote the $2M$ dimensional ground state multiplet of the Hamiltonian: $\mathcal{H}(k)|n(k)\rangle =$

$E_n(k)|n(k)\rangle$.^{11,12)} Assuming that the many-body energy gap is finite, we focus on topological invariants under the $U(2M)$ transformation

$$\psi(k) \rightarrow \psi(k)U(k), \quad U(k) \in U(2M). \quad (1)$$

As discussed,^{2,27)} the pfaffian defined by $p(k) = \text{pf} \Psi^\dagger(\mathcal{T}\Psi)$ characterizes the topological phases of \mathcal{T} invariant systems. To be precise, the systems belong to topological insulator if the number of zeros of the pfaffian in half the Brillouin zone is 1 (mod 2), and belong to simple insulator otherwise. This number has been referred to as Z_2 invariant. It should be noted that under eq. (1), the pfaffian $p(k)$ transforms as $p(k) \rightarrow e^{-i\phi(k)}p(k)$, where $\phi(k)$ is the $U(1)$ part of $U(2M)$ defined through the relation $e^{i\phi(k)} \equiv \det U(k)$.

Recently, Fu and Kane²⁴⁾ have shown that the Z_2 invariant is expressed alternatively by

$$D = \frac{1}{2\pi i} \left[\oint_{\partial \mathcal{B}^-} A - \int_{\mathcal{B}^-} F \right], \quad (2)$$

where $\mathcal{B}^- = [-\pi, \pi] \otimes [-\pi, 0]$ (see Fig. 1), and where A and F is, respectively, the Berry gauge potential and associated field strength defined by $A = \text{Tr} \psi^\dagger d\psi$ and $F = dA$.^{11,12)} Notice that the gauge transformation (1) yields $A \rightarrow A + id\phi$. This implies that the gauge of the Berry gauge potential can be fixed by the condition that the pfaffian




Fig. 1. (Color online) Left: The Brillouin zone, where shaded region denotes \mathcal{B}^- . The thick lines indicate the boundary of \mathcal{B}^- . The integration over \mathcal{C}_j gives a winding number. Right: A lattice on the Brillouin zone. The sites in \mathcal{B}_s^\pm are enclosed by thin lines (The sites in \mathcal{B}_s^- , \mathcal{B}_s^+ , and \mathcal{B}_s^0 are denoted by blue, red, and black circles, respectively). The shaded region denotes the plaquettes in \mathcal{B}^- .

$p(k)$ is real positive. Note also that $A(-k) = A(k)$ holds in this gauge. This is a kind of \mathcal{T} constraint, as stressed by Fu and Kane.²⁴ The zeros of $p(k)$ thus serve as an obstruction of the gauge fixing.²⁸

In systems with breaking \mathcal{T} symmetry like QH effect, such an obstruction gives in general a nontrivial Chern number. Contrary to this, in systems under consideration, the Chern number always vanishes due to \mathcal{T} invariance. Even in this case, an obstruction occurs in the Brillouin zone as long as the zeros of the pfaffian exist. Since the zeros occur at the time reversed pairs of points $\pm k_j^*$, the vortices around these pairs are opposite and therefore cancel each other, giving vanishing Chern number. Nevertheless the sum of vorticities in half the Brillouin zone, e.g., in \mathcal{B}^- , just gives the number of zeros of $p(k)$ (mod 2). Imagine, for example, that two zeros exist in \mathcal{B}^- . Since they are generically first order zeros, the winding numbers are ± 1 . Then their sum is restricted to ± 2 and 0, which can be denoted as “0 mod 2”. It thus turns out that the Fu–Kane formula (2) counts the vorticities in half the Brillouin zone. So far we have discussed in a specific gauge, but in any other gauge, D changes by 2, provided that the gauge keeps \mathcal{T} constraint. Therefore, D is indeed a Z_2 topological invariant. It has also a topological stability against small perturbation as long as the many-body gap is finite. As we will show below, this expression for Z_2 invariant is convenient for numerical computations.

Define a lattice on the Brillouin zone,

$$k_\ell = \pi(j_1/N_1, j_2/N_2), \quad j_\mu = -N_\mu, \dots, N_\mu. \quad (3)$$

The sites labeled by k_ℓ are divided into three sets, \mathcal{B}_s^\pm and \mathcal{T} invariant sites \mathcal{B}_s^0 denoted by red, blue and black circles in Fig. 1, respectively. Here, \mathcal{T} invariant sites are specified by the property that $\mathcal{T}H(k_\ell)\mathcal{T}^{-1} = H(k_\ell)$. As a \mathcal{T} constraint, we choose the states at $-k_\ell \in \mathcal{B}_s^+$ as their Kramers doublets at $k_\ell \in \mathcal{B}_s^-$. Suppose that at k_ℓ the spectrum is arranged as $\varepsilon_n(k_\ell) \leq \varepsilon_{n+1}(k_\ell)$. Then the states at $-k_\ell$ can be constrained as

$$|n(-k_\ell)\rangle = \mathcal{T}|n(k_\ell)\rangle, \quad \text{for } k_\ell \in \mathcal{B}_s^-. \quad (4)$$

On the other hand, both of the Kramers doublets are included in \mathcal{B}_s^0 . The spectrum in this set can be arranged in general as $\varepsilon_{2n-1}(k) = \varepsilon_{2n}(k) \leq \varepsilon_{2n+1}(k) \dots$. Therefore, we enforce the constraint

$$|2n(k_\ell)\rangle = \mathcal{T}|2n-1(k_\ell)\rangle, \quad \text{for } k_\ell \in \mathcal{B}_s^0. \quad (5)$$

With these constrained states, we define a link variable

$$U_\mu(k_\ell) = \mathcal{N}_\mu^{-1}(k_\ell) \det \psi^\dagger(k_\ell) \psi(k_\ell + \hat{\mu}), \quad (6)$$

where $\mathcal{N}_\mu(k_\ell) = |\det \psi^\dagger(k_\ell) \psi(k_\ell + \hat{\mu})|$, and associated field strength through a plaquette variable

$$F_{12}(k_\ell) = \ln U_1(k_\ell) U_2(k_\ell + \hat{1}) U_1^{-1}(k_\ell + \hat{2}) U_2^{-1}(k_\ell), \quad (7)$$

where F_{12} is defined within the branch $F_{12}/i \in (-\pi, \pi)$.

The sum of F_{12} over \mathcal{B}^- can be written as a similar formula to eq. (2). To see this, it is convenient to define a gauge potential via $A_\mu(k_\ell) = \ln U_\mu(k_\ell)$ also in the branch $A_\mu(k_\ell)/i \in (-\pi, \pi)$. Then the field strength can be rewritten as

$$F_{12}(k_\ell) = \Delta_1 A_2(k_\ell) - \Delta_2 A_1(k_\ell) + 2\pi i n_{12}(k_\ell), \quad (8)$$

where *integral* field $n_{12}(k_\ell)$ has been introduced so as to match the branches of both sides.^{25,34,35} Thus, we reach

$$\sum_{k_\ell \in \mathcal{B}^-} F_{12}(k_\ell) = \sum_{k_\ell \in \mathcal{B}^-} A_1(k_\ell) + 2\pi i \sum_{k_\ell \in \mathcal{B}^-} n_{12}(k_\ell), \quad (9)$$

where the sums of F_{12} and of n_{12} are over the plaquettes in the shaded region denoted by \mathcal{B}^- in Fig. 1. The sum of A_μ is over the links of the boundary of \mathcal{B}^- specified by thick lines in Fig. 1. Therefore, a lattice version of D is

$$D_L \equiv \frac{1}{2\pi i} \left[\sum_{k_\ell \in \partial \mathcal{B}^-} A_1(k_\ell) - \sum_{k_\ell \in \mathcal{B}^-} F_{12}(k_\ell) \right] = - \sum_{k_\ell \in \mathcal{B}^-} n_{12}(k_\ell). \quad (10)$$

This formula for the Z_2 invariants is one of the main results of this paper. Indeed this formula has the following desired properties. Firstly, it is strictly integral. Secondly, though the ground state multiplet can be mixed by eq. (1), it is $SU(2M)$ invariant. Finally, it changes by 2 under the remaining $U(1)$ transformation, and hence, it is Z_2 invariant. The last property will be proved elsewhere, though it is not difficult.

In 3D, it has been shown that the phases of \mathcal{T} invariant systems are classified by four independent Z_2 invariants.^{20–22} To compute them, let us define six two-dimensional tori, according to Moore and Balents.²¹ For example, fix the third momentum to $k_3 = 0$ or π , then we have two tori spanned by k_1 and k_2 which we denote Z_0 and Z_π torus, respectively. Applying the previous techniques, we can compute two Z_2 invariants D_L which are referred to as z_0 and z_π . In the same way, we have six invariants $x_0, x_\pi, y_0, y_\pi, z_0$, and z_π living on six tori $X_0, X_\pi, Y_0, Y_\pi, Z_0$, and Z_π , respectively. There are two constraints, however: $x_0 x_\pi = y_0 y_\pi = z_0 z_\pi$ (mod 2), and therefore, four invariants among six are independent.²¹ According to Fu *et al.*,²⁰ we choose them as $\nu_0 = x_0 x_\pi, \nu_1 = x_\pi, \nu_2 = y_\pi$, and $\nu_3 = z_\pi$, and denote them as $\nu_0; (\nu_1 \nu_2 \nu_3)$. As is known in the QH effects, non-trivial structures of topological ordered states are hidden in the bulk and play physical roles near the boundaries as characteristic edge states.²⁹ Based on the principle, by investigating the relationship between the Z_2 invariants and surface states, Fu *et al.* have clarified that there are basically three phases; simple band insulator, weak topological insulator (WTI) which is topological but weak against disorder, and more robust strong topological insulator (STI).²⁰

Recently, Murakami¹⁹ has pointed out the possibility of QSH effect in Bi. Though Bi is a semimetal, the valence band and conduction band keep the direct gap throughout the Brillouin zone. Fu *et al.* have studied solvable tight-binding models with the diamond structure, and predicted that the valence band of Bi is characterized by the WTI phase specified 0;(111), based on the observation that the structure of Bi can be viewed as an adiabatically distorted cubic lattice toward the diamond lattice. However, since a realistic tight-binding model including s and p orbitals with nearest neighbor, second neighbor, and third neighbor hoppings has indeed complicated band structure, we calculate the Z_2 invariants directly for heavy group V elements.

In what follows, we investigate real materials by the tight-binding models in ref. 36. We first discuss the phase of Bi




Fig. 2. The n -field configurations for Bi (left two panels) and Sb (right two panels) computed by the gauge that the pfaffian is real positive. The first and third (second and fourth) show the configurations on the Z_0 (Z_π) torus. The white and black circles denote $n_{12} = 1$ and -1 , respectively, while the blank denotes 0. These read $z_0 = 2$ and $z_\pi = 0$ for Bi, and $z_0 = 0$ and $z_\pi = 1$ for Sb.




Fig. 3. (Color online) Phase diagrams of Bi (left) and Sb (right) as functions of $V_{pp\sigma}$ and $V_{pp\pi}$. Other parameters are the same as those in ref. 36. The white points indicate the position of the parameters for Bi and Sb in ref. 36.

which is attracting much interest. We show in Fig. 2 examples of the n -field configuration computed for Bi. Though these calculations are for rather coarse 10×10 lattice, we have checked that finer ones indeed reproduce the same Z_2 invariants and our formula is actually convergent even in this mesh size. For Bi, these figures tell that $z_0 = z_\pi = 0 \pmod{2}$. The other Z_2 invariants are also $0 \pmod{2}$, and it turns out that the valence bands of Bi in 3D is specified by $0;(000)$ phase. This result is contradictory to the conjecture by Fu *et al.* mentioned-above. This suggests that along adiabatic distortion of the lattice, some topological changes should occur. Indeed, a slight change of the Slater–Koster parameters can lead to different phases. Among adjustable 14 parameters,³⁶⁾ crucial ones may be $V_{pp\sigma}$ and $V_{pp\pi}$, nearest neighbor hopping parameters between p orbitals. We show in Fig. 3 the phase diagram of Bi to discuss the stability of the phase. This diagram tells that Bi is located in a small island of $0;(000)$ phase embedded in $1;(111)$ phase. We also understand this feature from a small direct gap of Bi, 12 meV, at the L point.³⁶⁾ With varying the parameters, this gap soon closes and the phase of Bi changes from trivial phase into STI phase. We conclude that Bi in 3D dose not show the QSH effect, though it locates quite near the phase boundary with STI.

On the other hand, decreasing the thickness, a semimetal–semiconductor transition occurs, and Murakami has suggested that Bi thin film would be in QSH phase.¹⁹⁾ To study the quasi 2D systems, and also to clarify the discrepancy between our result and the conjecture by Fu *et al.*, we next investigate the effects of dimensionality on the present




Fig. 4. (Color online) Band structure of Bi (upper) and Sb (lower). Bi: The solid-lines (blue) are energies (eV) at $f = 0.5$ and the dotted-lines (red) are at $f = 0.1$. Sb: The solid-lines (blue) at $f = 0.7$ and the dotted-lines (red) at $f = 0.1$. There are other bands around -10 eV associated mainly with s orbitals which are omitted in these figures.




Fig. 5. (Color online) Phase diagrams of Bi (upper panel) and Sb (lower panel) for $f = 0.1$ as functions of $V_{pp\sigma}$ and $V_{pp\pi}$.

model. We replace the Slater–Koster parameters V'_α ($\alpha = ss\sigma, sp\pi, pp\sigma, ppp\pi$) for second neighbor hopping in ref. 36 by fV'_α with a uniform factor f . This factor f can effectively control the dimensionality into [111] direction, interpolating between Murakami’s model at $f = 0$ and the 3D model at $f = 1$.

We show in Fig. 4 the band structure of Bi with $f = 0.5$ and 0.1. At $f = 1$ (see ref. 36), the overlap energy (indirect gap) is $\Delta E = -12$ meV. With decreasing f , a semimetal–semiconductor transition occurs at $f \sim 0.99$. Figure 4 confirms that Bi is indeed a semiconductor at $f = 0.5$ and 0.1 whose overlap energy is $\Delta E = 56$ and 90 meV, respectively. Near $f = 0.993$, the phase of Bi changes from 0;(000) into 1;(111). With further decreasing f and enhancing the two-dimensionality, topological change occurs again near $f \sim 0.223$, and the system becomes 0;(111), as shown in Fig. 5. This is just the phase predicted by Fu *et al.*²⁰ Therefore, we suggest that the adiabatic distortion of the diamond lattice leads to Bi thin film, and along the change of the dimensionality, the adiabatic distortion does not work, giving rise to gap-closing and resultant topological changes. We also conjecture that STI phase is very stable along the change of f , and could be observed by experiments.

Sb is also a semimetal with a larger gap at the L point.³⁶ We show in Fig. 3 the phase diagram of Sb. It turns out that Sb belongs to the 1;(111) phase even in 3D. Its location is far from the phase boundary with 0;(000) and therefore, it is rather stable. We show in Fig. 4 the band structure of Sb. With decreasing f , a semimetal–semiconductor transition also occurs at $f \sim 0.89$. Along the change of f , topological change occurs once: Near $f \sim 0.54$, the phase changes from 1;(111) into 0;(000), and no 0;(111) phase is observed throughout. Therefore, the phase of Sb thin film is 0;(000), different from Bi. In Fig. 5, we show the phase diagram of Sb for $f = 0.1$. However, it should be stressed that with appropriate thickness, $0.54 \leq f \leq 0.89$, Sb is a semiconductor in STI phase and hence should show QSH effect.

Finally, we comment on the relationship between the method presented in this paper and the previous one in ref. 27. While in the present calculation link variables are defined with respect to the momentum, the previous calculation has been implemented with respect to twist angles by imposing a spin-dependent twisted boundary condition. For systems with appropriate strength of spin–orbit coupling, the present computation is more efficient, but for systems with very small spin–orbit coupling as well as with inversion symmetry, the previous computation by the

use of the twisted boundary condition gives more reliable results. In this sense, both methods are complementary to each other. Details will be published elsewhere.

We also mention that recently Fu and Kane³⁷ have reached the similar conclusion of the phases of Bi and Sb by making the use of inversion symmetry of the system. We stress here that our method can apply to any systems, even without inversion symmetry.

This work was supported in part by Grants-in-Aid for Scientific Research (Nos. 17540347 and 18540365) from the Japan Society for the Promotion of Science and on Priority Areas (No. 18043007) from the Ministry of Education, Culture, Sports, Science and Technology. YH was also supported in part by the Sumitomo foundation.

- 1) C. L. Kane and E. J. Mele: *Phys. Rev. Lett.* **95** (2005) 226801.
- 2) C. L. Kane and E. J. Mele: *Phys. Rev. Lett.* **95** (2005) 146802.
- 3) B. A. Bernevig and S.-C. Zhang: *Phys. Rev. Lett.* **96** (2006) 106802.
- 4) X.-L. Qi, Y.-S. Wu, and S.-C. Zhang: *Phys. Rev. B* **74** (2006) 085308.
- 5) L. Sheng, D. N. Sheng, C. S. Ting, and F. D. M. Haldane: *Phys. Rev. Lett.* **95** (2005) 136602.
- 6) S. Murakami, N. Nagaosa, and S.-C. Zhang: *Science* **301** (2003) 1348; S. Murakami, N. Nagaosa, and S.-C. Zhang: *Phys. Rev. Lett.* **93** (2004) 156804.
- 7) J. Sinova, D. Culcer, Q. Niu, N. A. Sinitsyn, T. Jungwirth, and A. H. MacDonald: *Phys. Rev. Lett.* **92** (2004) 126603.
- 8) Y. K. Kato, R. C. Myers, A. C. Gossard, and D. D. Awschalom: *Science* **306** (2004) 1910.
- 9) J. Wunderlich, B. Kästner, J. Sinova, and T. Jungwirth: *Phys. Rev. Lett.* **94** (2005) 047204.
- 10) X. G. Wen: *Phys. Rev. B* **40** (1989) 7387.
- 11) Y. Hatsugai: *J. Phys. Soc. Jpn.* **73** (2004) 2604.
- 12) Y. Hatsugai: *J. Phys. Soc. Jpn.* **74** (2005) 1374.
- 13) D. J. Thouless, M. Kohmoto, M. P. Nightingale, and M. den Nijs: *Phys. Rev. Lett.* **49** (1982) 405.
- 14) M. Kohmoto: *Ann. Phys. (N.Y.)* **160** (1985) 343.
- 15) M. F. Atiyah and I. M. Singer: *Ann. Math.* **93** (1971) 139.
- 16) E. Witten: *Phys. Lett. B* **117** (1982) 324.
- 17) Y. Yao, F. Ye, X.-L. Qi, S.-C. Ahang, and Z. Fang: *Phys. Rev. B* **75** (2007) 041401.
- 18) H. Min, J. E. Hill, N. A. Sinitsyn, B. R. Sahu, L. Kleinman, and A. H. MacDonald: *Phys. Rev. B* **74** (2006) 165310.
- 19) S. Murakami: *Phys. Rev. Lett.* **97** (2006) 236805.
- 20) L. Fu, C. L. Kane, and E. J. Mele: *Phys. Rev. Lett.* **98** (2007) 106803.
- 21) J. E. Moore and L. Balents: *Phys. Rev. B* **75** (2007) 121306.
- 22) R. Roy: cond-mat/0607531.
- 23) This is in sharp contrast to the usual quantum Hall effect in 3D, in which three Chern numbers specify the states. See, e.g., M. Kohmoto, B. I. Halperin, and Y.-S. Wu: *Phys. Rev. B* **45** (1992) 13488; A.-Z. Ezzine de Blas and F. Axel: *J. Phys.: Condens. Matter* **16** (2004) 7673.
- 24) L. Fu and C. L. Kane: *Phys. Rev. B* **74** (2006) 195312.
- 25) T. Fukui, Y. Hatsugai, and H. Suzuki: *J. Phys. Soc. Jpn.* **74** (2005) 1674.

- 26) D. N. Sheng, Z. Y. Weng, L. Sheng, and F. D. M. Haldane: *Phys. Rev. Lett.* **97** (2006) 036808.
- 27) T. Fukui and Y. Hatsugai: *Phys. Rev. B* **75** (2007) 121403.
- 28) R. Roy: cond-mat/0604211.
- 29) Y. Hatsugai: *Phys. Rev. Lett.* **71** (1993) 3697.
- 30) M. Lüscher: *Commun. Math. Phys.* **85** (1982) 39.
- 31) A. Phillips: *Ann. Phys. (N.Y.)* **161** (1985) 399.
- 32) A. Phillips and D. Stone: *Commun. Math. Phys.* **103** (1986) 599.
- 33) A. Phillips and D. Stone: *Commun. Math. Phys.* **131** (1990) 255.
- 34) M. Lüscher: *Nucl. Phys. B* **549** (1999) 295.
- 35) T. Fujiwara, H. Suzuki, and K. Wu: *Prog. Theor. Phys.* **105** (2001) 789.
- 36) Y. Liu and R. R. Allen: *Phys. Rev. B* **52** (1995) 1566.
- 37) L. Fu and C. L. Kane: cond-mat/0611341.